

## TECHNICAL DATASHEET

### 1665

(Resin 1663 + Hardener 1664)

#### Description

1665 is a non-sagging, two-part methyl methacrylate adhesive designed for structural bonding of thermoplastic, metal, and composite assemblies. Combined at a 10:1 (V:V) mixing ratio, it has a working time of 3 to 6 minutes. 50% of the final strength (at 23°C) will be achieved already within 15 to 18 minutes. 1665 is mainly used as an universal grade for industrial applications where composites are involved. Normally it does not require any surface preparation. It is often used in following industries: Household appliance (white ware), advertising panels, traffic guidance systems, electronic and electrical engineering, vehicle industry, furnishment, windows and doors, bus-, truck-, rail and car industry, boat and ship construction.

#### Advantages

- Good adhesion to a wide range of materials
- Non-dropping paste
- Bridges gap up to 10 mm
- Minimum gap 75 µm (Spacer)
- Excellent resistance against dynamic loads
- Optically visible hardening process – colour changes from blue to green
- Resistant against outside conditions and humidity
- 100% reactive compound

#### Product data


Chemical base	Methyl methacrylate adhesive
Curing system	2-Component-System
Mixing ratio by volume	10 : 1 (Resin 1663 : Hardener 1664)
Colour (after curing)	Olive green

**Physical properties (uncured):**

Viscosity	Resin	1663	~100'000 mPa·s
	Hardener	1664	~50'000 mPa·s
Density	Resin	1663	0.99 g/cm <sup>3</sup>
	Hardener	1664	1.15 g/cm <sup>3</sup>
Colour	Resin	1663	Off-white
	Hardener	1664	Blue
Shelf life			12 month at 4 – 23 °C
Flashpoint			10°C
Gap filling			Up to 10 mm
Minimum gap / Spacer			75 µm

**Curing properties:**

Application temperature	+10 °C to +40 °C
Open time at 23°C	3 – 6 minutes
Fixture time at 23°C [~1 N/mm <sup>2</sup> ]	8 – 13 minutes
Functional strength at 23°C [~10 N/mm <sup>2</sup> ]	~15 minutes
Final strength at 23°C	12 hours



**Physical properties (cured):**

E Modulus (DIN EN ISO 178)  
after 24 h at 23°C

~ 450 MPa

Tensile strength (ISO 527-2/1A)  
after 24 h at 23°C

~ 15 N/mm<sup>2</sup>

Elongation at break (ISO 527-2/1A)  
after 24 h at 23°C

~ 100 %

Shore D

~ 67

Usage temperature

- 55°C to + 120°C

**Lap shear strength (DIN EN 1465)**

Curing: 24 hours at 23 °C, test temperature 23 °C, metals corundum blasted

Steel

> 20 N/mm<sup>2</sup>

Steel-Glass

> 10 N/mm<sup>2</sup> (X)

Aluminium

> 19 N/mm<sup>2</sup>

GFRP

> 17 N/mm<sup>2</sup> (X)

ABS

> 5 N/mm<sup>2</sup> (X)

PC

> 6 N/mm<sup>2</sup> (X)

PVC

> 7 N/mm<sup>2</sup> (X)

PMMA

> 6 N/mm<sup>2</sup> (X)

(X) = Failure of test specimen

**Chemical resistance**

Excellent in

Hydrocarbons

Acidic solutions (pH 3 – 10)

Alkaline solutions (pH 3 – 10)

Salt solutions

Unstable in

Polar solvents

Strong acidic/alkaline solutions

### Handling and storage

Due to the high reactivity of the product and the exothermic curing process, never mix bigger amount of the components. The heat might evaporate parts of the formulation and cause strong smell. Do not waste exceeded material in plastic containers, because of the danger of melting.

Slight serum formation may occur during storage.

The serum does not imply any quality issues and can be ejected when levelling the cartridge before first use.

### Precautions

For your own safety, please refer to the information of the concerned MSDS and for the correct handling the "user instructions".

The information in this data sheet is based on the results of our research and experience. However, the suggestions herein concerning the use, application, and processing of the products (collectively, „the methods“) **are non-binding recommendations only**. It is the user's sole responsibility to determine the suitability and safety of these methods, based on the user's particular purpose in using the products. Before relying on the reliability and safety of any parts that are bonded using the products, it is extremely important that the user test the reliability and safety of the parts that are bonded. Failure to do so could result in serious personal injury. Because of the use of the products are within the purchaser's sole control, Kisling Corporation specifically disclaims all warranties, express or implied, including warranties of merchantability or fitness for a particular purpose, arising from the sale or use of the products described herein. Kisling Corporation specifically disclaims any liability for consequential, incidental, or other damages of any kind, including lost profits. Kisling Corporation's liability for damages shall not exceed the purchase price of the products used.

TIS\_1665\_e/PC/28.01.2022